

PATENT Customer No. 22,852 Attorney Docket No. 7991.0006-00

## IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

În re Application of:

Bomi M. Bilimoria

Group Art Unit: 1712

Application No.: 09/870,442

Examiner: R. Lovering

Filed: May 31, 2001

For:

METHODS FOR IMPROVING THE HIGH AND LOW SHEAR

RHEOLOGY OF MINERAL SLURRIES AND THE PRODUCTS

**DERIVED THEREFROM** 

Commissioner for Patents

P.O. Box 1450

Alexandria, VA 22313-1450

Sir:

## TRANSMITTAL LETTER

Enclosed is a Revised Amendment, including an Appendix, in reply to the Notice of Non-Compliant Amendment (37 CFR 1.121) dated May 1, 2003.

Please grant any extensions of time required to enter this revision and charge any additional required fees to our deposit account 06-0916.

By:

Dated: May 12, 2003

Brian M. Burn

Reg. No. 44,455

FINNEGAN HENDERSON FARABOW GARRETT & DUNNER LLP

1300 l Street, NW Washington, DC 20005 202.408.4000 Fax 202.408.4400 www.finnegan.com AECEIVED AND TO THE



PATENT

Customer No. 22,852

Attorney Docket No.: 7991.0006-00

## IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

Bomi M. Bilimoria

Application No.: 09/870,442

Filed: May 31, 2001

METHODS FOR IMPROVING THE For:

> HIGH AND LOW SHEAR RHEOLOGY OF MINERAL SLURRIES AND THE PRODUCTS DERIVED THEREFROM

Assistant Commissioner for Patents Washington, DC 20231

Sir:

Group Art Unit: 1712

Examiner: R. LOVERING

**AMENDMENT UNDER 37 C.F.R. §** 

In reply to the Office Action dated October 25, 2002, the period for re been extended three months to April 25, 2003 by a petition and fee filed concurrently herewith, Applicant respectfully requests reconsideration and reexamination of the application in view of the following amendment and remarks.

## IN THE SPECIFICATION:

Please cancel paragraphs [045] – [048] and replace with the following amended text:

1300 I Street. Washington, DC 20005 202.408.4000 Fax 202.408.4400 www.finnegan.com

[045] The acid flocculated and dried SPS was dispersed with a blend of sodium polyacrylate and soda ash at about pH = 8 at various solids concentrations. The 0.5-gallon samples were milled/liquid worked in a Kady mill for 20 minutes. The samples were then dried in an air oven overnight keeping the temperature below 75°C.